

FLINTAG

PRODUCT CODE: 3606

DESCRIPTION: Angular crushed dried Thames flint. 97% crystalline silica.
Dried graded and dust free.

SPECIFIC USES: Skid resistance - pedestrian and vehicular, roads, bridge decks, service ramps.

PACKAGING: Available per kilogram and 25kg sacks.

PREPARATION OF SUBSTRATE: Depends upon use.

MIXING: Maybe added to flooring compounds to improve wear. Or broadcast onto the surface of resin coatings.

APPLICATION AND EQUIPMENT: Depends on use, normally broadcast into wet resin systems during cure cycle.

CURE SCHEDULE: Depends upon surface on to which flintag is applied, normally 24 hours before excess material is removed.

MATERIAL USAGE/ COVERAGE: As a "Broadcast to excess system" on floor surfaces 3 kg/m².
Otherwise approximately 200-300 gms/m² as a skid resistant dressing.

CURED PROPERTIES: Extremely hard skid resistant surfaces, wear depends upon the resin/cement surface to which the flintag adheres

CLEANING TOOLS: Not applicable

The site conditions and equipment required when using individual Rotafix products are specific for each project. Only advice given by Rotafix in writing will be considered as part of our contractual liability.

The information in this document is based on practical tests, but given without guarantee insomuch as methods of use by others is beyond our control. Due to continuing development and improvements, it may be necessary to change without notice the material specification. All goods are sold subject to our Standard Conditions of Sale.

ROTAFIX, ROTAFIX HOUSE, ABERCRAF, SWANSEA SA9 1UR. U.K.

TEL: +44 (0) 1639 730481
e.mail: sales@rotafix.co.uk

FAX: +44 (0) 1639 730858
Website: www.rotafix.co.uk

SOUTHERN AREA CONTACT: TEL: +44 (0) 1442 243169 FAX: +44 (0) 1442 234901