

RESIWOOD® SYSTEMS

ROTAFIX GFRP PLATE AND STRIP

- PRODUCT CODE:** 3699 – 6mm x 40mm
3700 – 3mm x 40mm supplied per metre
- DESCRIPTION:** ROTAFIX GFRP Composite Technology is specifically designed for the fabrication of continuous fibre composites via a pultrusion process.
- PACKAGING:** Supplied in various widths, lengths and thicknesses.
- PREPARATION:** Surface preparation is of paramount importance. The plate should be mechanically abraded followed by a solvent wipe. For specific information consult our technical department.
- CHARACTERISTICS:** High strength and rigidity, good flexural stress behaviour, excellent static and dynamic load bearing capacity. Excellent corrosion resistance unaffected by wood tannin and both solvent and aqueous based timber preservatives and treatment. **ROTAFLEX PLATE** may be cut with standard 18 or 24 TPI hacksaw blades or ideally with a diamond bladed mechanical saw.

PHYSICAL PROPERTIES:

Glass content by volume	DIN EN 60	50 – 75 %
Density	DIN EN 53 479	2.0 KG/dm ²
Flexural Strength	DIN EN 63	1000 MPa
Tensile Modulus	DIN EN 61	40000 MPa
Compressive Strength	IN 53 454	450 MPa
Shear Strength	DIN EN 2344	20 – 40 MPa
Heat Deflection Temperature (under load)	Martens	200 deg C

- (1) NB typical properties were measured on 12mm Ø rod and a 20x2 mm strip.
- (2) 3 strips glued together.
- (3) 20mm width sample.
- (4) According to G” in DMS

- SPECIFIC USES:** Shear connectors for timber joints and connections. Strengthening and upgrading of timber structure components used in conjunction with the Resiwood range of adhesives.
- MATERIAL ESTIMATE:** Adhesive thicknesses should normally approximately 2mm min. Therefore material usage will be 2 litres/m² per 2 mm thick.

ROTAFIX PLATE does not present any particular hazard. When the PLATE is being cut or sawn there is a possibility of fibrous particles becoming airborne. Use wet cutting methods whenever possible. Always use appropriate protective clothing including safety goggles and suitable particulate face mask.

The information in this document is based on practical tests, but given without guarantee inasmuch as methods of use by others is beyond our control. Due to continuing development and improvements, it may be necessary to change without notice the material specification. All goods are sold subject to our Standard Conditions of Sale.

**The requirements for a Rotafix product(s) may be specific for an individual project.
Advice given by Rotafix can only be considered as part of the contract if it is provided in writing.**

RESIWOOD IS A REGISTERED TRADE MARKS OF ROTAFIX (NORTHERN) LTD.

**ROTAFIX, ROTAFIX HOUSE, ABERCRAF, SWANSEA SA9 1UR. U.K.
TEL: +44 (0)1639 730481 FAX: +44 (0)1639 730858
e.mail: sales@rotafix.co.uk Website: www.rotafix.co.uk**

SOUTHERN AREA CONTACT: TEL: +44 (0)1442 243169 FAX: +44 (0)1442 234901